

Product Data Sheet

K-KAT[®] 5218 Urethane Catalyst



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

K-KAT 5218 is an aluminum chelate complex catalyst for 2-component urethane coatings. It is effective for both ambient cure and baked systems. K-KAT 5218 is supplied in a reactive diluent for high solids applications. Provides superior pot life extension with the addition of 2,4-pentanedione.

ADVANTAGES:

- Fast tack free time
- Excellent viscosity stability/pot life
- Excellent exterior durability
- Effective with a variety of isocyanates and polyols
- Superior synergy with pot life extenders, such as 2,4-pentanedione

TYPICAL PROPERTIES:	Appearance	Clear to slightly hazy, amber liquid
	% Active (metal chelate)	65%
	Specific gravity, 25°C	1.1

SOLUBILITY: Soluble in alcohols, glycol ethers, esters, ketones and aromatic hydrocarbons. If 2,4-pentanedione is used as a pot life extender, it should be added to the polyol component then followed by the catalyst. It should not be pre-mixed with the K-KAT 5218.

APPLICATIONS:

- 2-Component urethane coatings
- Automotive topcoats
- High performance maintenance coatings
- Aerospace coatings
- Coatings for structural plastics

**TYPICAL USAGE
LEVELS:** 1.0 - 2.0% as supplied by weight on total resin solids. For better pot life 2,4-pentanedione can be added to paint formulations at a level of 1 - 1.5% weight on total resins solids. Refer to chart on the back of this page for more information on suggested usage levels.

INCORPORATION: Add to polyol component after the 2,4-pentanedione has been added.

SHELF LIFE: 18 months from the date of manufacture, when stored at ambient conditions in the original container.

**HANDLING &
STORAGE:** K-KAT 5218 is classified as a flammable liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. To prevent possible discoloration, product should be stored in lined or glass containers away from sunlight and excessive heat. Storage at lower temperature can lead to hazing. Warming product to 40°C (100°F) will restore clarity. Avoid contact with metals. Refer to MSDS for detailed information.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.


File: K-KAT 5218

Issue Date: 10/7/04

Supersedes: 1/21/04

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.

K-KAT 5218 Catalyst Concentration on TRS* DBTDL Replacement Level



* catalyst level as supplied based on total resin solids