

K-SPERSE[®] A504

Polymeric Pigment Dispersion



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

K-SPERSE A504 is a 100% active polymeric dispersant designed for use in 100% solids formulations including coatings, inks, pigment concentrates and plastics.

ADVANTAGES:

- Lower pigment paste viscosity and high pigment loading
- Excellent color development and high gloss
- Better clarity of transparent pigments
- Improved jetness and viscosity stability of carbon black dispersions
- Little or no effect on the cure of amino resins or isocyanates
- Compatible with a wide variety of resin systems
- No heat is necessary to dissolve it in polyacrylate UV formulations
- No interference in free radical UV systems

TYPICAL PROPERTIES:	Appearance	Clear to slightly hazy, viscous liquid
	% nonvolatile	99
	Gardner Color	9
	Acid #	28
	ICI Viscosity, poise at 75 °C	22
	Specific gravity, 25°C	1.0

SOLUBILITY: Soluble in acrylates, ketones, esters, ethers, aromatic hydrocarbons and butanol. Partially soluble in aliphatic hydrocarbons, isopropanol, and ethanol. Insoluble in water.

APPLICATIONS: K-SPERSE A504 is recommended for organic and inorganic pigments in a wide variety of resins, including; acrylates, alkyds, acrylics, polyesters, polyurethanes and aldehydes. It is especially effective for pigments with high surface areas, such as high color carbon blacks, phthalocyanine blue, quinacridone and perylene reds.

TYPICAL USAGE LEVELS:

For high color carbon black:
Weight % dispersant on pigment weight = pigment surface area(m²/g) x 0.14
For other pigments:
Weight % dispersant on pigment weight = pigment surface area(m²/g) x 0.33
It is strongly recommended that a ladder study be run, since the optimum level of dispersant depends on the type of pigment, resin and solvent used in each specific formulation.

INCORPORATION: K-SPERSE A504 should be dissolved in the mill base prior to pigment addition.

SHELF LIFE: 12 months from the date of manufacture, when stored at ambient conditions in the original container.


HANDLING & STORAGE: Safe handling of this product should include the use of safety glasses and gloves. Refer to MSDS for detailed information. This product may be heated up to 60 °C for easy handling. Avoid long periods of air exposure at elevated temperature as the product may darken.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.

Application tips

1) Viscosity of K-SPERSE® A504 vs. temperature:

This product by itself has a Newtonian behavior. Figure 1 shows its viscosity curve vs. temperature.



2) Stability of K-SPERSE A504 in acrylates

A 20% solution of K-SPERSE A504 in propoxylated neopentyl glycol diacrylate (Sartomer SR 9003) was made via moderate agitation at room temperature. The solution remains clear after 4 weeks storage at 5 °C.

2) Dispersion example of K-SPERSE A504 for UV cure

Table 1: Carbon black dispersion with A504. 120 min dispersing on a shaker with ¼ inch steel beads.

Material	Parts by weight
K-SPERSE A504	9.0
SARTOMER® SR 9003	81.0
MONARCH® 1300	10.0
Total	100.0
Brookfield viscosity at 25 °C after particle size reduction to less than 5 µm on Hegman gauge	
At 10 rpm	252 cps
At 100 rpm	226 cps

SARTOMER SR 9003, a propoxylated neopentyl glycol diacrylate supplied by Sartomer Company, West Chester, PA.

MONARCH 1300, a high color carbon black pigment with surface area of 560 m²/g supplied by Cabot Corp., Billerica, MA.

