

NACORR[®] 4426 Rust & Corrosion Inhibitor



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

NACORR 4426 is an emulsifiable corrosion inhibiting additive that provides excellent rust and corrosion prevention in waterborne emulsion coatings. It is a proprietary preparation of a sodium salt of an aromatic sulfonic acid and polymers.

ADVANTAGES: Excellent salt fog and humidity protection
Excellent stability in emulsion systems
Effective on steel, galvanized steel and aluminum
Especially effective in low solids waterborne systems

TYPICAL PROPERTIES:	Appearance	Light brown viscous liquid
	Viscosity, 40°C	2775 cps
	Density, 25°C	0.99 g/ml
	Weight Per Gallon, 25°C	8.3 Lbs.
	Flashpoint, COC	>100°C (>212°F)

APPLICATIONS: Emulsion based protective coatings and low solids waterborne systems.

TYPICAL USAGE LEVELS: 4-10% based on the total weight of paint if used as the sole anti-corrosive agent. When used in combination with other types of corrosion inhibiting pigments, NACORR 4426 should be added at 25-50% of the total anti-corrosive pigment loading.

INCORPORATION: NACORR 4426 should be post-added to the coating with good shear/agitation.

SHELF LIFE: 18 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: Avoid breathing vapors. Keep the container tightly closed. Store at room temperature away from direct sunlight. For further information, please consult the Material Safety Data Sheet.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.