

# Product Data Sheet

## NA-LUBE<sup>®</sup> KR-010



Science Road  
Norwalk, CT 06852  
(800) 431-7900  
Fax: (203) 866-0425  
E-Mail: lad@kingindustries.com

**NA-LUBE KR-010** is a specialty additive for high performance lubricants offering outstanding solubility plus excellent hydrolytic and thermo-oxidative stability.

### CHEMICAL

**COMPOSITION:** Proprietary alkylated aromatic.

**APPEARANCE:** Light amber liquid.

### TYPICAL

<b>PROPERTIES:</b>	Viscosity @ 40°C (ASTM D 445, DIN 51 550)	72 mm <sup>2</sup> /s (cSt)
	Viscosity @ 100°C (ASTM D 445, DIN 51 550)	9.2 mm <sup>2</sup> /s (cSt)
	Viscosity Index (Calculated)	103
	Pour Point (ASTM D 97)	-48°C (54.4°F)
	Aniline Point (ASTM D 611)	60°C (140°F)
	Density @ 25°C (ASTM D 4052)	0.89
	Weight Per Gallon @ 25°C	7.4 lbs
	Flash Point, COC (ASTM D 92, DIN 51 376)	220°C (428°F)

Note: The above analytical data are not specifications.

<b>APPLICATIONS:</b>	Aviation Hydraulic Fluids	Compressor Oils
	Crankcase Oils	Greases
	High Temperature Turbine Oils	Refrigeration Oils
	Other High Performance Applications	Gear Oils

**NA-LUBE KR-010** is a synthetic alkyl aromatic additive with excellent thermo-oxidative and hydrolytic stability. **NA-LUBE KR-010** can be used as a solubility modifier in formulations blended with low polarity base oils or severely hydrotreated base stocks to enhance additive response. The recommended treat level of **NA-LUBE KR-010** as a solubility modifier and as a performance enhancer is between 5.0% and 20.0% depending on the application. **NA-LUBE KR-010** can also be used as a major base fluid for high temperature applications requiring exceptional thermo-oxidative stability.

- ADVANTAGES:**
- \* **Base oil solubility modifier**
  - \* **Improves additive response**
  - \* **Excellent thermo-oxidative stability**
  - \* **Excellent hydrolytic stability**

(see reverse side)

## NA-LUBE<sup>®</sup> KR-010

- SOLUBILITY:** Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended that the solubility in the base oils used and the compatibility with other additives be verified.
- STANDARD PACKAGING:** 400 lbs (181 kg) closed head drum.
- STORAGE CONDITIONS:** Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)
- SHELF LIFE:** Minimum of 24 months from the date of manufacture, when stored at the above conditions in the original container.
- HANDLING:** Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Material Safety Data Sheet (MSDS) for **NA-LUBE KR-010**.
- REGISTRATION:** Please refer to Section 15 of the Material Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.  
Science Road  
Norwalk, CT 06852-0588  
Tel: 203-866-5551  
Fax: 203-866-0425  
E-mail: LAD@kingindustries.com

King Industries International, Inc.  
Noordkade 64, 2741 EZ Waddinxveen  
The Netherlands  
Tel: +31-182-631360  
Fax: +31-182-621002  
E-mail: info@kingintl.nl

v:\lad\Technical Literature\CumtTDS\NALUBE\KR010\_01  
Revision date: 27 AUG 2004

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.