

Product Data Sheet

NA-SUL[®] CA-1122 (Formerly KX1122)



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-0425
E-Mail: lad@kingindustries.com

NA-SUL CA-1122 is a high performance liquid rust and corrosion inhibitor for rust preventives and lubricants. **NA-SUL CA-1122** offers excellent solubility in highly paraffinic oils, polyalphaolefins (PAO), and many esters and vegetable oils. It has a low viscosity and does not contain wax, resulting in low odor and blending without adding heat. Contamination with alkaline materials or large amounts of water should be avoided*.

CHEMICAL

COMPOSITION: Calcium dinonylnaphthalenesulfonate/carboxylate in light mineral oil.

APPEARANCE: Clear brown low viscosity liquid.

TYPICAL

PROPERTIES:	Calcium Content	2.4%
	Acid Number (ASTM D 4739)	45 mg KOH/g
	Viscosity @ 100°C (ASTM D 445, DIN 51550)	28 mm ² /s (cSt)
	Density @ 15.6°C (ASTM D 4052)	0.98 g/ml
	Weight Per Gallon @ 25°C	8.2 lbs
	Flash Point, COC (ASTM D 92, DIN 51376)	165°C (329°F)
	Moisture Content (ASTM E 1064)	< 0.1%

Note: The above data are not specifications.

	<u>Typical Treat Levels</u>
APPLICATIONS: Rust Preventive Fluids	1.00% - 15.0%
Circulating Oils	0.05% - 1.0%
Greases	0.50% - 3.0%
Industrial and Automotive Gear Oils	0.10% - 1.0%

NA-SUL CA-1122 is a highly effective liquid rust and corrosion inhibitor when used in a variety of petroleum and synthetic lubricants. It outperforms most additive systems containing wax or other high melting materials in Salt Fog testing (ASTM B 117). It has excellent solubility in base fluids such as highly processed paraffinic oils, PAO, and vegetable oils.

ADVANTAGES:

- * Excellent rust inhibitor
- * Free flowing liquid, no melting required
- * Low odor, does not contain petroleum oxidates
- * Excellent solubility in highly paraffinic base oils and PAO
- * Non-staining on steel

(see reverse side)

NA-SUL[®] CA-1122
(Formerly KX1122)

TEST RESULTS: Technical reports are available from King Industries and can be requested by contacting the offices shown below.

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD PACKAGING: 420 lbs (191 kg) closed head drum.

STORAGE CONDITIONS: Store in a cool dry place away from any direct sources of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Not determined.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Material Safety Data Sheet (MSDS) for **NA-SUL CA-1122**.

* **NA-SUL CA-1122** has an acid value, which can result in the formation of gels or other unwanted by-products when contaminated with alkaline cleaners, metalworking fluids, or other alkaline process chemicals. If contaminated with significant amounts of water, a film or gel can gradually develop at the interface between the organic layer containing **NA-SUL CA-1122** and the aqueous layer. If testing shows incompatibility with alkaline chemicals that are likely to contaminate **NA-SUL CA-1122** solutions or if significant, prolonged water contact is probable **NA-SUL CA-1089** should be considered as the rust preventive additive in place of **NA-SUL CA-1122**.

REGISTRATION: Please refer to Section 15 of the Material Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425
E-mail: LAD@kingindustries.com

King Industries International, Inc.
Noordkade 64, 2741 EZ Waddinxveen
The Netherlands
Tel: +31-182-631360
Fax: +31-182-621002
E-mail: info@kingintl.nl

NA-SUL[®] is a registered trademark of King Industries, Inc.

v:\lad\TechnicalLiterature\CurmtDTS\NASUL\NASUL CA1122_02
Revision date: 27 JUL 2004

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.