

# Product Data Sheet

## NA-SUL<sup>®</sup> CA-1089 (Formerly KX1089)



Science Road  
Norwalk, CT 06852  
(800) 431-7900  
Fax: (203) 866-0425  
E-Mail: lad@kingindustries.com

**NA-SUL CA-1089** is a premium rust inhibitor for petroleum and synthetic lubricants, rust preventive fluids and metalworking specialties. It provides excellent demulsibility and filterability, both dry and wet, and is compatible with a wide range of additives and base stocks.

### CHEMICAL

**COMPOSITION:** Calcium alkyl naphthalenesulfonate/carboxylate complex in light mineral oil.

**APPEARANCE:** Clear brown viscous liquid.

### TYPICAL

<b>PROPERTIES:</b>	Calcium Content	2.2%
	Viscosity @ 40°C (ASTM D 445, DIN 51 550)	2500 mm <sup>2</sup> /s (cSt)
	Viscosity @ 100°C (ASTM D 445, DIN 51 550)	36 mm <sup>2</sup> /s (cSt)
	Density @ 15.6°C (ASTM D 4052)	0.96 g/ml
	Weight Per Gallon @ 25°C	8.0 lbs
	Flash Point, COC (ASTM D 92, DIN 51 376)	165°C (329°F)

Note: The above analytical data are not specifications.

	<u>Typical Treat Levels</u>
<b>APPLICATIONS:</b> Hydraulic Fluids (HF-0, HF-2)	0.05% - 0.5%
Circulating Oils	0.05% - 1.0%
Paper Machine Oils	0.25% - 1.0%
Rust Preventives	1.00% - 15.0%
Dewatering Fluids	1.00% - 10.0%

**NA-SUL CA-1089** can be used in a wide variety of industrial lubricant applications where excellent rust protection, filterability and water resistance are required. **NA-SUL CA-1089** is highly recommended for use in hydraulic fluids meeting the Denison HF-0 specification. **NA-SUL CA-1089** is also ideally suited for formulating paper machine oils and circulating oils where good filterability, anticorrosion, thermal stability and demulsification properties are required.

**ADVANTAGES:**

- \* Excellent rust inhibitor with outstanding demulsification properties
- \* Excellent filterability, both dry and wet
- \* Excellent thermal and hydrolytic stability
- \* Excellent solubility in highly paraffinic base stocks
- \* Resists gelling when contaminated with water

(see reverse side)

**NA-SUL<sup>®</sup> CA-1089**  
(Formerly KX1089)

**TEST RESULTS:** Technical reports are available from King Industries and can be requested by contacting the offices shown below.

**SOLUBILITY:** Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

**STANDARD PACKAGING:** 420 lbs (191 kg) closed head drum.

**STORAGE CONDITIONS:** Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

**SHELF LIFE:** Best if used within 3 years from date of manufacture.

**HANDLING:** Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Material Safety Data Sheet (MSDS) for **NA-SUL CA-1089**.

**REGISTRATION:** Please refer to Section 15 of the Material Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.  
Science Road  
Norwalk, CT 06852-0588  
Tel: 203-866-5551  
Fax: 203-866-0425  
E-mail: LAD@kingindustries.com

King Industries International, Inc.  
Noordkade 64, 2741 EZ Waddinxveen  
The Netherlands  
Tel: +31-182-631360  
Fax: +31-182-621002  
E-mail: info@kingintl.nl

v:\lad\Technical Literature\CurrntDS\NASUL\NASUL CA1089\_05  
Revision date: 17 MAR 2005

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.