

Product Data Sheet

NA-LUBE[®] AO-242



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-0425
E-Mail: lad@kingindustries.com

NA-LUBE AO-242 is an ashless liquid phenolic high temperature antioxidant for petroleum and synthetic based automotive and industrial lubricants and greases.

CHEMICAL

COMPOSITION: Di-tert-butylphenol derivative.

APPEARANCE: Clear yellow to amber liquid.

TYPICAL

PROPERTIES:	Assay Content	99.4%
	Viscosity @ 40°C (ASTM D 445, DIN 51 550)	117 mm ² /s (cSt)
	Viscosity @ 100°C (ASTM D 445, DIN 51 550)	5 mm ² /s (cSt)
	Density @ 15.6°C (ASTM D 4052)	0.98 g/ml
	Weight Per Gallon @ 25°C	8.2 lbs
	Flash Point, COC (ASTM D 92, DIN 51 376)	148°C (298°F)

Note: The above analytical data are not specifications.

	<u>Typical Treat Levels</u>
APPLICATIONS:	
Hydraulic Oils	0.1% - 0.3%
Paper Machine Oils	0.1% - 0.5%
Circulating Oils	0.1% - 0.5%
Rust & Oxidation Oils	0.1% - 0.3%
Compressor Oils	0.3% - 1.0%
Industrial Gear Oils	0.2% - 0.4%
Automotive Gear Oils	0.2% - 0.4%
Polyglycol Based Products	0.5% - 1.0%

NA-LUBE AO-242 is a 100% active highly effective phenolic antioxidant. **NA-LUBE AO-242** possesses low volatility and low viscosity and therefore can easily be incorporated into all types of lubricants and greases. **NA-LUBE AO-242** provides superior oxidative protection and a reduction in sludge formation. The oxidation stability of industrial lubricants and greases can be increased significantly by using **NA-LUBE AO-242** in combination with aminic antioxidants such as NA-LUBE AO-110 or NA-LUBE AO-150 and appropriate yellow metal deactivators.

ADVANTAGES:

- * **Liquid, easy to handle**
- * **Low volatility**
- * **Excellent oxidation inhibitor**
- * **Low sludge formation**
- * **Light color**

(see reverse side)

NA-LUBE[®] AO-242

TEST RESULTS: Technical reports are available from King Industries and can be requested by contacting the offices shown below.

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD PACKAGING: 400 lbs (182 kg) closed head drum.

STORAGE CONDITIONS: Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Best if used within 2 years from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Material Safety Data Sheet (MSDS) for **NA-LUBE AO-242**.

REGISTRATION: Please refer to Section 15 of the Material Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425
E-mail: LAD@kingindustries.com

King Industries International, Inc.
Noordkade 64, 2741 EZ Waddinxveen
The Netherlands
Tel: +31-182-631360
Fax: +31-182-621002
E-mail: info@kingintl.nl

NA-LUBE[®] is a registered trademark of King Industries, Inc.

v:\lad\Technical Literature\CumtTDS\NALUBE AO\AO242_04
Revision date: 29 JUL 2004

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.