

Deovulc EG 3

INTRODUCTION: **Deovulc EG 3** is a blend of accelerators designed as a general purpose solution for EPDM.

CHEMICAL COMPOSITION: Synergistic blend of highly active accelerators.

APPEARANCE: Beige, non-dusting powder

TYPICAL PROPERTIES:

Total Sulfur (%), ASTM D 1552	30.5 – 33.5
Density @20°C (DIN ISO 787 part 10A)	1.34 – 1.46 g/cm ³

Note: The above analytical data are not specifications.

ADVANTAGES: Deovulc EG 3 is an excellent accelerator for general EPDM applications requiring a medium cure rate and an average compression set with non-staining and non-blooming requirements. Typical dosage is 3-5 phr for black loaded compounds or 5-6 phr for light colored compounds with 1-2 phr sulfur. No additional accelerators are required.

APPLICATION: Wide range for non-blooming, non-staining EPDM articles.

STANDARD: PACKAGING 20 kgs in cardboard box with PE liner

STORAGE: Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 25°C

SHELF LIFE: Min. one year in the originally sealed package under the recommended storage conditions

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Material Safety Data Sheet (MSDS) for **Deovulc EG 3**

REGISTRATION: Please refer to the Material Safety Data Sheet

Issued: 1/31/07