

Dispergum 40

- INTRODUCTION:** **Dispergum 40** is a zinc-free peptizer that is easily incorporated and dispersed in natural rubber and synthetic polymers.
- CHEMICAL COMPOSITION:** Proprietary oxidation catalyst combined with organic and inorganic additives
- APPEARANCE:** Blue black pellets
- TYPICAL PROPERTIES:**
- | | |
|--|-----------------------|
| Ash (%), 2hrs at 950°C, DIN EN ISO 3451-1 | 19.0 – 21.0 |
| Dropping point (°C), Mettler apparatus, DIN ISO 2176 | 92 - 102 |
| Density @20°C (DIN ISO 787 part 10A) | 1.2 g/cm ³ |
- Note: The above analytical data are not specifications.
- ADVANTAGES:** Dispergum 40 is soluble in rubber and therefore it incorporates and disperses with ease. The duration of the mastication process is drastically reduced by the high efficient oxidation catalyst at low doses. Additional benefits in extrusion applications and injection molding can be obtained through a pre-mastication step and no viscosity drift is observed under storage. Typical dosage is 0.1-1 phr.
- APPLICATION:** Peptizer for internal mixers at 90 - 180°C for natural rubber or synthetic polymers such as peptizable SBR, BR, and others.
- STANDARD: PACKAGING** 25 kgs in paper bags
- STORAGE:** Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 25°C
- SHELF LIFE:** Min. one year in the originally sealed package under the recommended storage conditions.
- HANDLING:** Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Material Safety Data Sheet (MSDS) for **Dispergum 40**
- REGISTRATION:** Please refer to the Material Safety Data Sheet

Issued: 1/31/07

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by the way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable, however, no guarantee or warranty of their accuracy is made. EXCEPT AS STATED. THERE ARE NO WARRANTIES, EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.