

Product Data Sheet

K-FLEX[®] A308 Polyester Polyol Preliminary Data Sheet



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

K-FLEX A308 is a low viscosity, 100% active, linear, saturated, aliphatic polyester diol with primary hydroxyl groups. This product was designed as a flexibility modifier for acrylic/isocyanate and acrylic/melamine systems. The low viscosity combined with higher hydroxyl number gives good hardness and adhesion while allowing lower VOC levels.

APPLICATIONS:
Automotive OEM
Automotive refinish
Aerospace
Industrial maintenance
Plastic coatings

ADVANTAGES:
Improved flexibility
Good balance of surface dry/pot life in 2K PU
Light color
Abrasion resistance
No acid functionality

TYPICAL PROPERTIES:	Appearance	Clear liquid
	% Active	100
	Viscosity, cPs, 25° C	1,500
	Hydroxyl number	260
	Hydroxyl equiv. weight	216
	Weight per gallon, 25°C	9.2 lb.
	Gardner color	1

SOLUBILITY:
Soluble in alcohols, esters, ketones, xylene, Aromatic 100 and Aromatic 150.
Partially soluble in mineral spirits. Insoluble in water.

TYPICAL USAGE LEVELS:
5-25% replacement of primary backbone resin

SHELF LIFE:
Minimum of 24 months from date of manufacture, when stored in the original container at ambient conditions.

HANDLING & STORAGE:
Store in a cool, dry location. Please consult Material Safety Data Sheet for further information.

REGULATORY:
Please refer to Section 15 of the Material Safety Data Sheet for information.