

Product Data Sheet

NACURE® 4054 Weak Acid Catalyst



Science Road
Norwalk, CT 06852
United States
+1-203-866-5551
www.kingindustries.com

NACURE 4054 is a hydrophobic alkyl acid phosphate catalyst supplied at 50% active in isobutanol. It is a weak acid catalyst recommended for use with high -NH/polymeric melamines and phenolic crosslinkers.

ADVANTAGES: Excellent solubility
Good package stability
Good adhesion and salt spray resistance
Excellent water resistance compared to other phosphate catalysts

TYPICAL PROPERTIES:	Appearance	Clear, straw liquid
	% Active	50
	Acid value	160
	Volatile	Isobutanol
	Weight per gallon @ 25°C (lbs)	7.5

SOLUBILITY: Soluble in alcohols, glycol ethers, glycols, esters, ketones and aromatic and aliphatic hydrocarbons. Insoluble in water.

APPLICATIONS: Particularly effective with polymeric melamines for;
Appliance finishes
Automotive topcoats and primers
General industrials
Wood coatings

TYPICAL USAGE LEVELS: 0.5 - 3.0% as supplied on total resin solids.

INCORPORATION: May be added to the coating with agitation as supplied or pre-diluted with alcohol.

SHELF LIFE: 24 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: NACURE 4054 is classified as a flammable and corrosive liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Refer to SDS for detailed information.

REGULATORY: Please refer to Section 15 of the Safety Data Sheet for information.

File: N-4054_2

Issue Date: 11/6/2019

Supersedes: 12/22/17

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.