

Product Data Sheet

NACURE[®] 5925 Blocked Catalyst



Science Road
Norwalk, CT 06852
United States
+1-203-866-5551
www.kingindustries.com

NACURE 5925 is an amine neutralized DDBSA catalyst. It is formulated to meet the requirements of FDA 21 CFR Section 175.300 (paragraph (b) (3) xiii (a) (b) and xii (a) (b)) concerning chemicals for use in resinous and polymeric coatings.

ADVANTAGES: Very light color
Excellent solubility characteristics
Good exterior durability
Complies with FDA CFR 21, Section 175.300

TYPICAL PROPERTIES:	Appearance	Clear, light amber liquid
	% Active	25
	pH (1:1 with DI water)	8.0
	Volatile	Isopropanol
	Weight per gallon @ 25°C (lbs)	7.3

SOLUBILITY: Soluble in water, alcohols, glycol ethers, glycols, esters, ketones, aromatic and aliphatic hydrocarbons.

APPLICATIONS: Can coatings
Automotive topcoats
General industrials
Waterborne coatings

TYPICAL USAGE LEVELS: 0.5 to 2.0% as supplied on total resin solids.

INCORPORATION: May be added to the coating with agitation as supplied or pre-diluted with alcohol.

SHELF LIFE: 18 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: NACURE 5925 is classified as a flammable liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Refer to Safety Data Sheet for detailed information.

REGULATORY: Please refer to Section 15 of the Safety Data Sheet for information.

File: NACURE 5925_2

Issue Date: 12/22/17

Supersedes: 09/02/09

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.