

Product Data Sheet

NACURE® XP-357 Blocked Catalyst



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

NACURE XP-357 is an amine neutralized p-TSA catalyst. It is recommended for applications which require rapid cure response at temperatures as low as 200°F (93°C). It can be used in both aqueous and solventborne thermoset coatings.

ADVANTAGES: Formulated for rapid cure or short cure schedules.
Very low tendency to yellow

TYPICAL PROPERTIES:	Appearance	Clear, straw liquid
	% Active	20
	pH (1:1 with DI Water)	3.0
	Weight per gallon, 25°C	8.0 lbs.
	Volatile	Methanol

SOLUBILITY: Soluble in water, alcohols, esters, glycol ethers and aromatics. Partially soluble in ketones. Insoluble in aliphatic hydrocarbons.

APPLICATIONS: Wood coatings
Paper coatings
Plastic coatings
General industrial
Automotive basecoats

**TYPICAL USAGE
LEVELS:** 0.5 to 2.0% as supplied on total resin solids.

INCORPORATION: May be added to the coating with agitation as supplied or pre-diluted with alcohol.

SHELF LIFE: 12 months from the date of manufacture, when stored at ambient conditions in the original container.

**HANDLING &
STORAGE:** NACURE XP-357 is classified as a flammable liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Periodic venting of the container may be required to relieve pressure build-up. The Safety Data Sheet should be consulted prior to use. Product should be stored in lined or glass containers away from sunlight and excessive heat.

REGULATORY: Please refer to Section 15 of the Safety Data Sheet for information.

File: NACURE XP-357

Issue Date: 1/23/2019

Supersedes: 12/21/18

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.