

## NACURE<sup>®</sup> 155

Strong Acid Catalyst



NACURE 155 is a hydrophobic sulfonic acid catalyst based on dinonylnaphthalene disulfonic acid supplied as a 55% concentrate in isobutanol. Its primary use is as a catalyst for promoting the cure of hydroxy, carboxy and amide functional polymers with melamine and urea-formaldehyde crosslinking agents.

ADVANTAGES:	Excellent water, salt spray, detergent resistance Superior adhesion to a variety of substrates Low conductivity for electrostatic spray Soluble in aromatic hydrocarbons	
TYPICAL PROPERTIES:	Appearance % Active Acid value Volatile Weight per gallon @ 25°C (lbs)	Clear, amber liquid 55 115 Isobutanol 8.3
SOLUBILITY:	Soluble in alcohols, glycol ethers, glycols, esters, ketones and aromatic hydrocarbons. Insoluble in water and aliphatic hydrocarbons.	
APPLICATIONS:	Waterborne can coatings Coil coatings Automotive primers Appliance finishes Printing inks Electrostatic spray applications Electro coatings General industrial	
TYPICAL USAGE LEVELS:	0.5 to 2.0% as supplied on total resin solids.	
INCORPORATION:	May be added to the coating with agitation as supplied or pre-diluted with alcohol.	
SHELF LIFE:	24 months from the date of manufacture, when stored at ambient conditions in the original container.	
HANDLING & STORAGE:	NACURE 155 is classified as a flammable liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Product color will increase with age, particularly if stored at elevated temperatures. Refer to SDS for detailed information.	
REGULATORY:	Please refer to Section 15 of the Safety Data Sheet for information.	
File: NACURE 155_3	Issue Date: 11/6/2019	Supersedes: 12/22/17

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.