

DISPARLON

July 2018

DISPARLON AQH-810

(Rheology control agent for waterborne systems)

DISPARLON AQH-810 is a rheology control agent composed of a hybrid compound of a polyamide and an amide wax. DISPARLON AQH-810 forms a needle-like structure by itself in a coating system, and prevents settling and hard caking. Unlike general waterborne thickeners, DISPARLON AQH-810 can provide high thixotropic property without excess viscosity increasing. The coating solution containing DISPARLON AQH-810 has better thermo stability compared with general thickeners.

ADVANTAGES

- Excellent anti-settling property
- Imparts high thixotropic property without excess viscosity increasing
- Easy incorporation
- Excellent thermo stability

APPLICATIONS

DISPARLON AQH-810 can be used in a wide range of waterborne coating systems.

INCORPORATION

- Additive levels : 1.0 ~ 5.0 % by wt on total formulation.
Method : Can be added at each production stage. Post-addition at a final production stage with a dissolver is recommended.
Keep temperature from a room temperature up to 40 °C during dispersing.

TYPICAL PROPERTIES

Appearance	Yellow paste
Active matter	15% by wt.
Amine	N, N-dimethylethanolamine
Solvent	Water / Propylene glycol monomethyl ether
Acid value	8.7

STORAGE

- Keep from freezing. Freezing causes severe degradation of quality and performance.
- Do not heat. Store below 40°C. Heating causes degradation of quality and performance.



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2015 All Rights Reserved By Kusumoto Chemicals, Ltd.