

Additives for coatings and printing inks
DISPARLON[®]

July 18, 2014

DISPARLON[®] AQX-60

(Co-solvent free rheology control agent for waterborne systems)

DISPARLON AQX-60 is a co-solvent free rheology control agent composed of a polyamide. DISPARLON AQX-60 forms a network structure by interacting with paint components in a coating system, prevents settling and hard caking, and improves pigment orientation. Unlike general waterborne thickeners, DISPARLON AQX-60 can provide high thixotropic property without excess viscosity increasing.

ADVANTAGES

- Excellent anti-settling property
- Imparts high thixotropic property without excess viscosity increasing
- Easy incorporation
- Co-solvent free

APPLICATIONS

DISPARLON AQX-60 can be used in a wide range of waterborne coating systems.

INCORPORATION

Additive levels : 1.0~4.0% by wt on total formulation.

Method : Can be added at each production stage. Post-addition at a final production stage with a dissolver is recommended.

Keep temperature from a room temperature up to 40°C during dispersing.

TYPICAL PROPERTIES

Appearance	Yellow paste
Active matter	15% by wt.
Amine	N, N-dimethylethanolamine
Solvent	Water
Acid value	12.5

STORAGE

- Keep from freezing. Freezing causes degradation of quality and performance.
- Do not heat. Store below 40°C. Heating causes degradation of quality and performance.



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079