

## **DISPARLON BB-102**

(Anti-sagging/Anti-settling agent)

DISPARLON BB-102 is thixotropic agent based on amide wax pre-activated in Non-aromatic solvents.

DISPARLON BB-102 is very soft paste designed for easy incorporation by post-addition.

### **ADVANTAGES**

- Strong anti-sagging/ anti-settling effect
- Easy incorporation (No need to make Master-batch)
- Ready to use (No need for activation process)
- Improve orientation of metal pigment

### **APPLICATIONS**

DISPARLON BB-102 is recommended for most of solvent based systems such as plastics, wood, automotive, heavy duty, marine, architectural and industrial coatings.

### **INCORPORATION**

- Additive levels : Preferable dosage level per total formulation is 1.0 ~ 5.0 wt.% for anti-sagging and 0.5 ~ 2.0 wt.% for anti-settling. However, dosage level may fall out of these ranges depending on your formulation. The optimal level should be determined by your laboratory tests.
- Method : High speed dissolver is recommended.
- Dispersing temperature : Amide component may form particles if it is dissolved into a formulation and later precipitated during dispersing process. Standard dispersing temperature is between the room temperature and 50°C to prevent particle generation. Please be careful of the dispersing temperature because particles may occur at the upper side of the standard temperature range mentioned above if a formulation contains large amount of polar solvent.

### **TYPICAL PROPERTIES**

- Appearance : Light yellow paste
- Non-volatile matter : 10% by weight
- Solvent : Butyl acetate/ n-Butyl alcohol



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2009-2021 All Rights Reserved By Kusumoto Chemicals, Ltd.

## **STORAGE**

Particles may occur in the paste during storage at a low temperature less than 15°C because of the crystallization of its ingredients. In such case, please warm the vessel in a heating chamber at the temperature between 35°C and 40°C for 24 to 48 hours just before using it.

Store temperature: below 40°C. Storing above 40°C may cause degradation of quality and performance.  
(Thickening behavior may be changed. / Dispersibility may be deteriorated.)

## **CAUTION**

Amide wax may cause low surface tension. Please make sure to check recoatability especially in alkyd melamine or oil modified alkyd baking systems.



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

---

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2009-2021 All Rights Reserved By Kusumoto Chemicals, Ltd.