

DISPARLON

August 2018

DISPARLON L-1984N

(Leveling / Flow agent)

DISPARLON L-1984N is a silicone-free, non-ionic high molecular weight surface-active additive. DISPARLON L-1984N is 100% active, chemically stable and has excellent dispersibility in wide range of paint systems. DISPARLON L-1984N is utilized in the advanced paint technologies including high-solids coatings, Powder coatings and UV cured systems as surface modifiers.

ADVANTAGES

- Improve leveling and prevent cratering and pinholes.
- Improve film gloss with excellent compatibility with resins and by promoting pigment wetting, resulting in good dispersion.
- Act as defoamer.
- 100% solids and chemically stable; do not affect stability.
- No affect on physical properties of the film such as recoatability.
- Excellent dispersibility allows post addition.

APPLICATION

DISPARLON L-1984N can be used in almost all type of baking high-solids coatings, thermosetting powder coatings, UV curing systems, non-solvent coatings as well as conventional baking solvent based coatings and Unsaturated polyester coatings, particularly high-solids Polyester / Melamine and Acrylic / Melamine coatings for automotive.

INCORPORATION

For solvent based and high-solids coatings : 0.1 to 0.5% by weight of total formulation under stirring.
Post-addition on high-speed dissolver is recommended. Can be added any stage.

TYPICAL PROPERTIES

| | |
|-----------------------------|------------------------------|
| Appearance | Clear to light yellow liquid |
| Active content [%] | 100 |
| S.P. [—] | 8.89 |
| S.T. [Dyn/cm ²] | 29.4 |



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2004 All Rights Reserved By Kusumoto Chemicals, Ltd.