

Product  
Data  
Sheet

# K-CORR<sup>®</sup> G-1340



Science Road  
Norwalk, CT 06852  
(800) 431-7900  
Fax: (203) 866-0425  
E-Mail: lad@kingindustries.com

**K-CORR G-1340** is a proprietary zinc based rust inhibitor system developed for specialty grease applications as a replacement for zinc naphthenate.

## CHEMICAL

**COMPOSITION:** Proprietary preparation of zinc carboxylate.

**APPEARANCE:** Clear brown viscous liquid.

## TYPICAL

<b>PROPERTIES:</b>	Zinc Content	13.1%
	Viscosity @ 40°C (Black Pearl Plate)	12878 cSt
	Viscosity @ 100°C	135.4 cSt
	Density @ 15.6°C (ASTM D 4052)	1.064 g/cm <sup>3</sup>
	Weight Per Gallon @ 25°C	8.88 lbs
	Flash Point, COC (ASTM D 92, DIN 51 376)	> 100°C (212°F)

Note: The above analytical data are not specifications.

**APPLICATIONS:** Greases

Typical Treat Levels  
0.5% - 5%

**K-CORR G-1340** is a highly efficient rust inhibitor that is especially suitable to fulfill severe rust requirements in greases, e.g., Emcor test with 100% synthetic sea water and 3% NaCl solution.

**ADVANTAGES:**

- \* **Excellent rust protection under extreme conditions**
- \* **Good anti-wear performance**
- \* **Good thermal and oxidative stability**
- \* **Effective at very low treat levels**
- \* **Excellent compatibility with other functional additives**
- \* **Minimal effects on other grease properties**
- \* **Low odor**

(see reverse side)

# K-CORR® G-1340

**SOLUBILITY:** Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

**STANDARD PACKAGING:** 450 lbs (204 kg) open head drum.

**STORAGE CONDITIONS:** Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

**SHELF LIFE:** Best if used within 1 year from the date of manufacture.

**HANDLING:** Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **K-CORR G-1340**.

**REGISTRATION:** Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.  
Science Road  
Norwalk, CT 06852-0588  
Tel: 203-866-5551  
Fax: 203-866-0425  
E-mail: LAD@kingindustries.com

King Industries International, Inc.  
Science Park 402,  
1098 XH Amsterdam  
The Netherlands  
Tel: +31-20-723-1970  
E-mail: info@kingintl.nl

K-CORR® is a registered trademark of King Industries, Inc.

V:\lad\TechnicalLiterature\CumtPDS\K-CORR\G-1340\_02  
Revision date: 09 JUNE 2016

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.