

Product Data Sheet

K-CURE[®] 1040W Strong Acid Catalyst



Science Road
Norwalk, CT 06852 USA
Phone: +1 (203) 866-5551
Toll Free: (800) 431-7900
E-Mail: coatings@kingindustries.com

K-CURE 1040W is a very high quality para-Toluenesulfonic acid (p-TSA) catalyst that is dissolved in water.

ADVANTAGES:

- Fast cure
- Non-flammable
- Excellent weathering and exterior durability
- High gloss
- Easily incorporated into water systems

TYPICAL PROPERTIES:	Appearance	Clear, straw liquid
	% Active	40
	Acid Value	135
	Weight per gallon, 25°C	9.4
	Volatile	Water
	Gardner Color	1

SOLUBILITY: Soluble in water, alcohols, glycol ethers and glycols. Insoluble in esters, ketones, aromatic and aliphatic hydrocarbons

APPLICATIONS:

- Waterborne paper coatings
- Waterborne wood coatings
- Waterborne printing inks

TYPICAL USAGE LEVELS: 0.25 - 1.0 % as supplied on total resin solids.

INCORPORATION: May be added to the coating with agitation as supplied or pre-diluted with water.

SHELF LIFE: 24 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: K-CURE 1040 is classified as a corrosive liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Avoid contact with ferrous metal or mild steel. Refer to MSDS for detailed information.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.

File: K-1040W

Issue Date: 8/17/17

Supersedes: 4/29/02

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.