

Preliminary Data Sheet

K-KAT[®] XK-635



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

K-KAT XK-635 is a new non-tin catalyst recommended for solvent based or solvent free 2-component polyurethanes and 1-component blocked isocyanate systems.

ADVANTAGES: Good pot life in 2K PU systems
Good cure time characteristics
Non-yellowing
Excellent gloss retention

TYPICAL PROPERTIES:	Appearance	Light yellow liquid
	% Active	100.0
	Specific gravity, 25°C	1.14
	Weight per gallon, 25°C	9.5

SOLUBILITY: K-KAT XK-635 is soluble in ketones, esters and aromatic hydrocarbons. It is insoluble in water.

APPLICATIONS: K-KAT XK-635 can be used in ambient cured or force dried 2-component solvent based polyurethane systems. It can also be used in thermal cured 1-component blocked isocyanate systems.

TYPICAL USAGE LEVELS: 0.1 – 0.5% as supplied on total resin solids for 2-component polyurethane systems.
0.5 – 1.0% as supplied on total resin solids for blocked isocyanate systems.

INCORPORATION: K-KAT XK-635 can be added directly to the polyol component in 2K systems or to blocked isocyanate systems at anytime during the manufacturing process.

SHELF LIFE: 24 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: Product should be stored in a cool, dry environment away from sunlight and excessive heat. Consult the Material Safety Data Sheet prior to use.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.

File: K-KAT XK-635

Issue Date: 11/29/2011

Supersedes: