

K-CORR® G-1360



Science Road Norwalk, CT 06852 (800) 431-7900 Fax: (203) 866-0425 E-Mail: lad@kingindustries.com

K-CORR G-1360 is a proprietary zinc based rust inhibitor system developed for specialty grease applications as a replacement for zinc naphthenate.

CHEMICAL

COMPOSITION: Proprietary preparation of zinc carboxylate.

APPEARANCE: Clear brown viscous liquid.

TYPICAL

PROPERTIES: Zinc Content 8.2%

 Phosphorus Content
 1.1%

 Viscosity @ 40°C (ASTM D445, DIN 51550)
 815 cSt

 Viscosity @ 100°C (ASTM D445, DIN 51550)
 31 cSt

 Density @ 15.6°C (ASTM D4052)
 0.996 g/cm³

Weight Per Gallon @ 25°C 8.3 lbs

Flash Point, COC (ASTM D92, DIN 51 376) >130°C (266°F)

Note: The above analytical data are not specifications.

Typical Treat Levels

APPLICATIONS: Greases 0.5% - 5%

K-CORR G-1360 is a highly efficient rust inhibitor that is especially suitable to fulfill severe rust requirements in greases, e.g., Emcor test with 100% synthetic sea water and 3% NaCl solution.

ADVANTAGES: * Excellent rust protection under extreme conditions

* Good anti-wear performance

- * Good thermal and oxidative stability
- * Effective at very low treat levels
- * Excellent compatibility with other functional additives
- * Minimal effects on other grease properties
- * Low odor
- * Easy to handle

(see reverse side)

K-CORR® G-1360

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common

solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD

PACKAGING: 440 lbs (200 kg) open head drum.

STORAGE

CONDITIONS: Store in a cool, dry place away from any direct source of heat and moisture.

Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Best if used within 18 months from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional

information, it is advised to consult the Safety Data Sheet (SDS) for

K-CORR G-1360.

REGISTRATION: Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

WWW.KINGINDUSTRIES.COM

Global Headquarters Tech. Services, R&D and Sales

King Industries, Inc.
Science Road

Norwalk, CT 06852-0588 Tel: 203-866-5551

Fax: 203-866-0425

European Tech. Sales Office

King Industries International, Inc. Science Park 402 1098 XH Amsterdam The Netherlands

Tel: +31-20-723-1970

China Sales Office

Dalian Mingruida Technical Consulting Co., Ltd Building 51, 20 Shuxiang Street Dalian, China

Tel: +86-15941108485

K-CORR® is a registered trademark of King Industries, Inc.

V:\lad\TechnicalLiterature\CurntPDS\K-CORR\G-1360_03 Revision date: 6 JUL 2023

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.