

Product Data Sheet

NA-LUBE[®] AW-6330



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-0425
E-Mail: lad@kingindustries.com

NA-LUBE AW-6330 is a multifunctional ashless additive for industrial and automotive lubricants, greases, and metalworking fluids. **NA-LUBE AW-6330** exhibits excellent extreme pressure and antiwear properties. Additionally, it imparts antioxidation properties to lubricants and greases.

CHEMICAL

COMPOSITION: Proprietary preparation of phosphorus-sulfur containing chemistry.

APPEARANCE: Clear amber moderately viscous liquid.

TYPICAL

PROPERTIES:	Sulfur Content	10.6%
	Phosphorus Content	5.1%
	Color (ASTM D1500 neat)	1.5
	Viscosity @ 40°C (ASTM D445, DIN 51 550)	20 mm ² /s (cSt)
	Viscosity @ 100°C (ASTM D445, DIN 5 1550)	3 mm ² /s (cSt)
	Density @ 25°C (ASTM D4052)	1.01 g/ml
	Weight Per Gallon @ 25°C	8.4 lbs
	Mineral Oil Content	none
	Flash Point, COC (ASTM D92, DIN 51376)	163°C (325°F)

Note: The above analytical data are not specifications.

		<u>Typical Treat Levels</u>
APPLICATIONS:	Hydraulic Fluids	0.15% - 1.0%
	Circulating Oils	0.15% - 1.0%
	Paper Machine Oils	0.20% - 1.5%
	Industrial and Automotive Gear Oils	0.30% - 1.5%
	Metalworking Fluids	0.20% - 6.0%

NA-LUBE AW-6330 is a multifunctional ashless lubricant additive exhibiting excellent extreme pressure, antiwear, and antioxidation properties. **NA-LUBE AW-6330** can be used as an alternative to zinc dialkyldithiophosphates as an antiwear additive in hydraulic oil and industrial gear formulations. For formulating metalworking fluids, it is recommended to use **NA-LUBE AW-6330** in conjunction with light color, low-odor, sulfur carriers such as King Industries' NA-LUBE[®] EP-5000 Series.

(see reverse side)

NA-LUBE® AW-6330

ADVANTAGES:

- * **Ashless multifunctional lubricant additive**
- * **Outstanding extreme pressure/antiwear performance**
- * **Good antioxidation properties**
- * **Good solubility in mineral oils and synthetic base stocks**

TEST RESULTS: Technical reports are available from King Industries and can be requested by contacting the offices shown below.

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD PACKAGING: 450 lbs (204 kg) closed head drum.

STORAGE CONDITIONS: Store in a cool dry place away from any direct sources of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Best if used within 2 years from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **NA-LUBE AW-6330**.

REGISTRATION: Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

WWW.KINGINDUSTRIES.COM

Global Headquarters

Tech. Services, R&D and Sales

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425

European Tech. Sales Office

King Industries International, Inc.
Science Park 402
1098 XH Amsterdam
The Netherlands
Tel: +31-20-723-1970

China Sales Office

Dalian Mingruida Technical Consulting Co., Ltd
Building 51, 20 Shuxiang Street
Dalian, China
Tel: +86-15941108485

NA-LUBE® is a registered trademark of King Industries, Inc.

v:\lad\TechnicalLiterature\Currnt\TDS\NA-LUBE\AW-6330_09
Revision date: 11 JUL 2023

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.