

Product Data Sheet

NA-LUBE[®] EP-5310



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-0425
E-Mail: lad@kingindustries.com

NA-LUBE EP-5310 is a light colored, low odor inactive sulfurized fatty acid ester/fatty oil with excellent extreme pressure properties.

CHEMICAL

COMPOSITION: Sulfurized fatty acid ester/fatty vegetable oil.

APPEARANCE: Brown clear liquid.

TYPICAL

PROPERTIES:	Sulfur Content	10.0%
	Active Sulfur Content (ASTM D 1662)	<1.0%
	Color (ASTM D 1500 neat)	5.5
	Viscosity @ 40°C (ASTM D 445, DIN 51 550)	240 mm ² /s (cSt)
	Density @ 20.0°C (ASTM D 941)	0.94 g/ml
	Weight Per Gallon @ 25°C	8.09 lbs.
	Flash Point, COC (ASTM D 92, DIN 51 376)	195°C (383°F)

Note: The above analytical data are not specifications.

		<u>Typical Treat Levels</u>
APPLICATIONS:	Metalworking Fluids	4.0% - 10.0%
	Water Miscible Metalworking Concentrates	5.0% - 20.0%
	Industrial Gear Oils	1.0% - 1.2%
	Slideway Oils	1.0% - 5.0%
	Automotive Gear Oils	1.0% - 2.0%
	Greases	1.0% - 5.0%

NA-LUBE EP-5310 is a low odor, light colored sulfur carrier based on fatty acid ester/fatty oil chemistry. It has excellent solubility in naphthenic and Group I and II mineral oils and ester basestocks for industrial lubricants, greases and neat metalworking fluids. **NA-LUBE EP-5310's** novel chemistry provides improved lubricity over similar inactive sulfur fatty acid ester type extreme pressure additives. When used in combination with appropriate metal-containing or ashless phosphorus-containing antiwear or lubricity additives, **NA-LUBE EP-5310** provides excellent extreme pressure properties and offers an alternative to chlorinated paraffins in metalworking fluids, especially for cutting operations.

- ADVANTAGES:**
- * **Good extreme pressure properties**
 - * **Light color, low odor, inactive**
 - * **Usable with ferrous and non-ferrous metals**
 - * **Easy handling, low viscosity**
 - * **Good solubility in Group I, II and naphthenic base oils**

(see reverse side)

NA-LUBE[®] EP-5310

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD PACKAGING: 441 lbs (200 kg) closed head drum.

STORAGE CONDITIONS: Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 30°C (86°F)

SHELF LIFE: Best if used within 1 year from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **NA-LUBE EP-5310**.

REGISTRATION: Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425
E-mail: LAD@kingindustries.com

King Industries International, Inc.
Science Park 402,
1098 XH Amsterdam
The Netherlands
Tel: +31-20-723-1970
E-mail: info@kingintl.nl

NA-LUBE[®] is a registered trademark of King Industries, Inc.

v:\lad\Technical Literature\CumtTDS\NALUBE EP\EP5310_03
Revision date: 18 MARCH 2015

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.