

NA-SUL BSN-HT is a high performance rust and corrosion inhibitor offering exceptional rust protection with outstanding high temperature stability and good demulsibility in petroleum and synthetic lubricants.

CHEMICAL

COMPOSITION: Barium dinonylnaphthalenesulfonate/carboxylate in light mineral oil.

APPEARANCE: Clear brown viscous liquid.

TYPICAL

PROPERTIES:	Barium Content	8.7%
	Viscosity @ 40°C (ASTM D 445, DIN 51 550)	3100 mm ² /s (cSt)
	Viscosity @ 100°C (ASTM D 445, DIN 51 550)	75 mm ² /s (cSt)
	Density @ 15.6°C (ASTM D 4052)	1.05 g/ml
	Weight Per Gallon @ 25°C	8.7 lbs
	Flash Point, COC (ASTM D 92, DIN 51 376)	175°C (347°F)

Note: The above analytical data are not specifications.

	<u>Typical Treat Levels</u>
APPLICATIONS: Rust Preventive Fluids	1.00% - 15.0%
Hydraulic Fluids	0.05% - 0.5%
Circulating Oils	0.05% - 1.0%
Paper Machine Oils	0.25% - 1.0%
Greases	0.50% - 3.0%
Industrial and Automotive Gear Oils	0.10% - 1.0%

NA-SUL BSN-HT is an excellent rust and corrosion inhibitor when used in a variety of petroleum and synthetic lubricants. In static high temperature aging tests, **NA-SUL BSN-HT** provides up to 100°C improvement in thermal stability over conventional sulfonates in polyol esters for aviation oils. **NA-SUL BSN-HT** is ideally suited for formulating hydraulic oils, circulating oils and gear oils where good anticorrosion, hydrolytic and thermal stability as well as outstanding demulsification properties are required. **NA-SUL BSN-HT** also exhibits outstanding additive compatibility and reduced moisture sensitivity.

ADVANTAGES:

- * Excellent rust inhibitor
- * Outstanding demulsibility
- * Excellent thermal and oxidative stability
- * Excellent solubility in highly paraffinic base stocks
- * Easy handling
- * Low odor

(see reverse side)

NA-SUL[®] BSN-HT

TEST RESULTS: Technical reports are available from King Industries and can be requested by contacting the offices shown below.

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD PACKAGING: 440 lbs (200 kg) closed head drum.

STORAGE CONDITIONS: Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Best if used within 3 years from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **NA-SUL BSN-HT**.

REGISTRATION: Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425
E-mail: LAD@kingindustries.com

King Industries International, Inc.
Science Park 402,
1098 XH Amsterdam
The Netherlands
Tel: +31-20-723-1970
E-mail: info@kingintl.nl

NA-SUL[®] is a registered trademark of King Industries, Inc.

v:\lad\Technical Literature\CurmtTDS\NASUL\BSN-HT_04
Revision date: 06 JUNE 2014

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.