

Product Data Sheet

DISPARLON[®] AQ-501 Anti-Popping/Defoaming Agent for Water-Based Systems



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

DISPARLON AQ-501 is an anti-popping and defoaming agent specifically designed for waterborne bake finishes. DISPARLON AQ-501 contains the same active ingredient as DISPARLON AQ-500, but does not contain any ethoxylated nonyl phenol.

ADVANTAGES: Eliminates entrapped air in bake systems, during cure.
Improves gloss and clarity of waterborne bake finishes.
Prevents pinholes and craters.

TYPICAL PROPERTIES:	Appearance	Clear light yellow liquid
	% Active	85
	Solvent	2 ethylhexanol

APPLICATIONS: DISPARLON AQ-501 is recommended for alkyd/melamine, acrylic/melamine and polyester/melamine water-based systems.

TYPICAL USAGE LEVELS: 0.3 to 1.0% based on total weight of paint.

INCORPORATION: Post-add and disperse uniformly under mild agitation. It can also be added to the pigment grind.

SHELF LIFE: 24 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: Keep the container tightly closed and store in a cool dry place. For further information please consult the Material Safety Data Sheet.

REGULATORY: All components of this product are listed or in compliance with U.S. TSCA.

* DISPARLON is a Trademark of Kusumoto Chemical Ltd., Tokyo, Japan

File:AQ-501

Issue Date: 11/03

Supersedes: NA

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.