

Product Data Sheet

NA-LUBE[®] AW-6110P

SAMPLE REQUEST



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-0425
E-Mail: lad@kingindustries.com

NA-LUBE AW-6110P is an ashless antiwear additive and rust inhibitor.

CHEMICAL

COMPOSITION: Amine salts of aliphatic phosphoric acid esters.

APPEARANCE: Light yellow viscous liquid.

TYPICAL

PROPERTIES:	Nitrogen Content	3.7%
	Phosphorus Content	5.3%
	Viscosity @ 40°C (ASTM D 445, DIN 51 550)	200 mm ² /s (cSt)
	Viscosity @ 100°C (ASTM D 445, DIN 51 550)	15 mm ² /s (cSt)
	Density @ 15.6°C (ASTM D 4052)	0.93 g/ml
	Weight Per Gallon @ 25°C	7.75 lbs
	Flash Point, COC (ASTM D 92, DIN 51 326)	> 100°C (212°F)

Note: The above analytical data are not specifications.

	<u>Typical Treat Levels</u>
APPLICATIONS: Metalworking Fluids	0.10% - 2.00%
Industrial Gear Oils	0.10% - 1.00%
Compressor Oils	0.10% - 0.50%
Turbine Oils	0.10% - 0.50%
Ashless Hydraulic Oils	0.10% - 0.50%
Rust and Oxidation Oils	0.10% - 0.50%

NA-LUBE AW-6110P is an ashless multifunctional additive that provides excellent antirust, antiwear and EP properties. It is especially suited for formulating ashless lubricants that require high load carrying capacity (FZG) and rust protection at low treat levels. **NA-LUBE AW-6110P** combined with a light colored, low odor sulfur carrier, such as NA-LUBE EP-5216, is a suitable alternative to chlorinated paraffins for use in metalworking fluids.

ADVANTAGES:

- * Multifunctional additive with excellent antirust, AW and EP properties
- * Light color, low odor
- * Easy to handle
- * Excellent solubility properties

(see reverse side)

NA-LUBE[®] AW-6110P

TEST RESULTS: Technical reports are available from King Industries and can be requested by contacting the offices shown below.

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD PACKAGING: 410 lbs (186 kg) closed head drum.

STORAGE CONDITIONS: Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Best if used within 12 months from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **NA-LUBE AW-6110P**.

REGISTRATION: Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425
E-mail: LAD@kingindustries.com

King Industries International, Inc.
Science Park 402,
1098 XH Amsterdam
The Netherlands
Tel: +31-20-723-1970
E-mail: info@kingintl.nl

NA-LUBE[®] is a registered trademark of King Industries, Inc.

v:\lad\TechnicalLiterature\CumtTDS\NALUBE\AW6110P_04
Revision date: 13 AUG 2015

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.