

Technical Report

Science Road, Norwalk, CT 06852 - (203) 866-5551
 Fax: (203) 866-0425 - Email: lad@kingindustries.com



NA-LUBE[®] EP-5665 Ashless Multifunctional Additive Performance in Grease

NA-LUBE EP-5665 is an ashless, multifunctional additive with excellent extreme pressure, antiwear and antioxidant properties. It is recommended for use in greases where heavy load carrying capability is required. Applications include steel mills, mining and construction equipment.

BASE GREASE	Lithium 12-Hydroxystearate			Lithium Complex
	1.0	2.0	3.0	3.0
% NA-LUBE EP-5665				
Four Ball Weld (ASTM D 2596) 1800 rpm, 25°C, 10 seconds OK Load / Weld Load (kgf)	315 / 400	500 / 620	620 / 800	620 / 800
Four Ball Wear (ASTM D 2266) Scar Diameter (mm) 1200rpm, 75°C, 40 kgf, 1 hour	0.78	0.70	0.64	0.62
Timken (ASTM D 2509) OK Load (lb)	--	< 30	40	50
Copper Corrosion (ASTM D 4048) 3 hours @ 100°C	1b	1b	1b	1b
Oxidation Stability (ASTM D 942) Pressure drop, 100 hours (psi) Pressure drop, 500 hours (psi)	-- --	4 15	3 9	3 10

The results shown reflect data generated by King Industries' Technical Service Laboratory. Actual results may vary depending on the additive package, base oil, and test equipment design.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
 Science Road
 Norwalk, CT 06852-0588
 Tel: 203-866-5551
 Fax: 203-866-0425
 E-mail: LAD@kingindustries.com

King Industries International, Inc.
 Science Park 402,
 1098 XH Amsterdam
 The Netherlands
 Tel: +31-20-723-1970
 E-mail: info@kingintl.nl

NA-LUBE[®] is a registered trademark of King Industries, Inc.

(see reverse side)

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.