

Name	F 17 ground	
Composition	rapeseed oil, cross-linked with sulphur, free of mineral oil	
Appearance	ground	
Analytical Values		
Total sulphur (%)	ASTM D 1552 (LECO)	16 - 19
Free sulphur (%)	Auler method	0.9 - 1.4
Acetone extract (%)	DIN ISO 1407	14 - 19
Ash, 2 h at 950 °C (%)	DIN EN ISO 3451-1	max. 0.2
Density at 20°C (g/cm ³)	DIN ISO 787 part 10 A	1.1
German Food Legislation (BfR recommendation XXI)	approved	
US Code of Federal Regulations, FDA - CFR Title 21, Part 177	listed	
Supply Form	25 kg in PE-bags	
Storage Stability		
In originally sealed package in cool and dry places	min. 1 year	
Application		
For coloured and black articles based on general purpose rubbers, especially extruded sections.		
Notes		
For detailed description of technological effects and dosages see DOG-Kontakt 38.		

Any technical consultation provided by us merely constitutes a guideline without any committal - even with regard to any third party's rights - and will not dispense from the client's examination of the products supplied by us. Processing operations, application and use of our products will be the client's exclusive responsibility. We guarantee the faultless quality of our goods, as defined in our General Terms of Sale and Delivery.

Valid 2004, March 19th