

Product
Data
Sheet

K-CORR[®] G-1086A

SAMPLE REQUEST



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-0425
E-Mail: lad@kingindustries.com

K-CORR G-1086A is a proprietary rust inhibitor system developed for industrial and automotive greases.

CHEMICAL

COMPOSITION: Proprietary preparation of alkylated organic acid/ester and zinc compound in light mineral oil.

APPEARANCE: Clear amber viscous liquid.

TYPICAL

PROPERTIES:	Zinc Content	9%
	Viscosity @ 40°C (ASTM D 445, DIN 51550)	6400 mm ² /s (cSt)
	Viscosity @ 100°C (ASTM D 445, DIN 51550)	130 mm ² /s (cSt)
	Density @ 15.6°C (ASTM D 4052)	1.0 g/ml
	Weight Per Gallon @ 25°C	8.6 lbs
	Mineral Oil Content	~ 23%
	Flash Point, COC (ASTM D 92, DIN 51376)	170°C (338°F)

Note: The above analytical data are not specifications.

APPLICATIONS:	Greases	<u>Typical Treat Levels</u> 0.7% - 5.0%
----------------------	---------	--

K-CORR G-1086A is a highly efficient rust and corrosion inhibitor that exhibits antiwear synergy with selected first intention antiwear and extreme pressure additives. **K-CORR G-1086A** is especially suitable to fulfill severe rust requirements in greases, e.g., Emcor test with 100% synthetic sea water and 3% NaCl solution.

ADVANTAGES:

- * Excellent rust and corrosion protection
- * Antiwear synergist with first intention EP/AW additives
- * Good thermal and oxidative stability
- * Excellent solubility in mineral oils, synthetic oils, and greases
- * Effective at very low treat levels
- * Excellent compatibility with all types of conventional functional additives
- * Easy to handle

(see reverse side)

K-CORR® G-1086A

TEST RESULTS: Technical reports are available from King Industries and can be requested by contacting the offices shown below.

SOLUBILITY: Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

STANDARD

PACKAGING: 440 lbs (200 kg) closed head drum.

STORAGE

CONDITIONS: Store in a cool dry place away from any direct sources of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

SHELF LIFE: Best if used within 18 months from the date of manufacture.

HANDLING: Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **K-CORR G-1086A**.

REGISTRATION: Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.
Science Road
Norwalk, CT 06852-0588
Tel: 203-866-5551
Fax: 203-866-0425
E-mail: LAD@kingindustries.com

King Industries International, Inc.
Science Park 402,
1098 XH Amsterdam
The Netherlands
Tel: +31-20-723-1970
E-mail: info@kingintl.nl

K-CORR® is a registered trademark of King Industries, Inc.

v:\lad\TechnicalLiterature\CumtTDS\KCORR\G1086A_06
Revision date: 09 JUNE 2016

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.