

K-KAT XK-640 is a versatile bismuth carboxylate catalyst designed for blocked isocyanate and two component urethane coatings. It can provide similar properties to standard tin catalysts without the environmental drawbacks. K-KAT XK-640 is designed to provide improved hydrolytic stability compared to other bismuth carboxylate catalysts.

ADVANTAGES: Can be used in ambient, force dry and bake systems
Excellent gloss retention
Excellent exterior durability

TYPICAL PROPERTIES:	Appearance	Clear, amber liquid
	% Metal	18
	Specific gravity, 25°C	1.12

SOLUBILITY: K-KAT XK-640 is soluble in aromatics, aliphatics and glycol ethers. It has limited solubility in esters and alcohols. K-KAT XK-640 is insoluble in water.

APPLICATIONS: K-KAT XK-640 is recommended for 2K and blocked isocyanate coatings. K-KAT XK-640 can replace many heavy metal and/or toxic catalysts used in the production of urethane elastomers, foams and coatings.

TYPICAL USAGE LEVELS: 0.05-0.2% as supplied on total resin solids for 2-component polyurethanes.
1.0-2.5% as supplied on total resin solids for blocked isocyanates.

INCORPORATION: K-KAT XK-640 can be added directly to a single component blocked isocyanate system or the polyol component of a 2K system.

SHELF LIFE: 24 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: Safe handling of this product should include the use of a respirator, safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. K-KAT XK-640 is sensitive to moisture; therefore, exposure to atmosphere during storage should be avoided. Product should be stored in a cool, dry environment away from sunlight and excessive heat. Consult the Material Safety Data Sheet prior to use.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.