

SAMPLE REQUEST

K-KAT XK-675 is a non-tin catalyst for silane polymers cured at ambient temperature for coatings, adhesives, sealants and elastomers.

ADVANTAGES:

- Excellent catalyst for the reaction of silane polymers at ambient cure temperature.
- Non-yellowing

TYPICAL PROPERTIES:	Appearance	Light amber liquid
	% Active	100.0
	Specific gravity, 25°C	0.98

SOLUBILITY: Soluble in glycol ethers, glycols, esters, ketones and aromatic hydrocarbons. Insoluble in water.

APPLICATIONS: K-KAT XK-675 can be used in ambient cured 1-component silane polymers.

TYPICAL USAGE LEVELS: 1.0– 3.0% as supplied based on total formulation weight.

INCORPORATION: K-KAT XK-675 can be added directly to the formulated 1-component silane system anytime during the manufacturing process.

SHELF LIFE: 24 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: Product should be stored in a cool, dry environment away from sunlight and excessive heat. Consult the Safety Data Sheet prior to use.

REGULATORY: Please refer to Section 15 of the Safety Data Sheet for information.

File: K-KAT XK-675

Issue Date: 2/27/2019

Supersedes: 1/31/2019