

# Product Data Sheet

## K-CORR<sup>®</sup> NF-200



Nonfood Compounds  
(Category Code: HX-1)  
(Registration #141124)



Science Road  
Norwalk, CT 06852  
(800) 431-7900  
Fax: (203) 866-0425  
E-Mail: lad@kingindustries.com

**SAMPLE REQUEST**

**K-CORR NF-200** is a premium ashless liquid yellow metal deactivator for industrial and automotive lubricants, greases and rust preventive fluids.

### CHEMICAL

**COMPOSITION:** Proprietary heterocyclic derivative.

**APPEARANCE:** Clear amber viscous liquid.

### TYPICAL

<b>PROPERTIES:</b> Viscosity @ 40°C (ASTM D 445, DIN 51550)	78 mm <sup>2</sup> /s (cSt)
Viscosity @ 100°C (ASTM D 445, DIN 51550)	6 mm <sup>2</sup> /s (cSt)
Density @ 15.6°C (ASTM D 4052)	0.95 g/ml
Weight Per Gallon @ 25°C	7.9 lbs
Flash Point, COC (ASTM D 92, DIN 51376)	170°C (338°F)

Note: The above analytical data are not specifications.

**APPLICATIONS:** **K-CORR NF-200** is an ashless, easy to handle, yellow metal deactivator for protecting copper and copper alloys against corrosion initiated by active sulfur. **K-CORR NF-200** protects oils from the catalytic pro-oxidant effects of dissolved copper ions by forming a protective barrier film on the copper surface. **K-CORR NF-200** can be used in all mineral oil based lubricants and most synthetic lubricants. Depending on the base oil type and other additives used, the recommended treat level of **K-CORR NF-200** is 0.03%-0.07% by weight.

**ADVANTAGES:**

- \* Compliance with the Food and Drug Administration Regulation 21 CFR 178.3570
- \* Synergistic with primary and secondary antioxidants
- \* Excellent thermal and hydrolytic stability
- \* Good demulsification properties
- \* Outstanding solubility in mineral oil and synthetic base stocks
- \* Good compatibility with other additives
- \* Low viscosity

(see reverse side)

# K-CORR<sup>®</sup> NF-200

**SOLUBILITY:** Soluble in petroleum and synthetic lubricant base stocks and most common solvents. Insoluble in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

**TEST RESULTS:** Technical reports are available from King Industries and can be requested by contacting the offices shown below.

**STANDARD PACKAGING:** 420 lbs (191 kg) closed head drum.

**STORAGE CONDITIONS:** Store in a cool dry place away from any direct sources of heat and moisture. Maximum recommended storage temperature: 46°C (115°F)

**SHELF LIFE:** Best if used within 18 months from the date of manufacture.

**HANDLING:** Avoid all personal contact. Observe good personal hygiene. For additional information, it is advised to consult the Safety Data Sheet (SDS) for **K-CORR NF-200**.

**REGISTRATION:** Please refer to Section 15 of the Safety Data Sheet for information.

For Samples or Technical Service, contact King Industries or your King representative.

King Industries, Inc.  
Science Road  
Norwalk, CT 06852-0588  
Tel: 203-866-5551  
Fax: 203-866-0425  
E-mail: LAD@kingindustries.com

King Industries International, Inc.  
Science Park 402,  
1098 XH Amsterdam  
The Netherlands  
Tel: +31-20-723-1970  
E-mail: info@kingintl.nl

K-CORR<sup>®</sup> is a registered trademark of King Industries, Inc.

v:\nad\TechnicalLiterature\CurmtPDS\KCORRNF200\_06  
Revision date: 23 NOV 2015

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.