

Additives for coatings and printing inks

DISPARLON[®]

May 2012

DISPARLON[®] AQ-607

(Rheology control agent for water-borne system)

DISPARLON AQ-607 is a polyamide based rheology control agent for water-borne systems. A 3-D network structure is formed by interaction of AQ-607 with the coating vehicle; as a result it prevents sagging and pigment settling. AQ-607 is different from traditional water-borne thickening agents since it has strong pseudoplasticity.

ADVANTAGES

- Prevents hard caking by minimizing pigment settling
- Excellent humidity resistance
- Orientation of metallic and pearlescent pigments
- Highly shear thinning

TYPICAL PROPERTIES

Appearance	Yellowish brown to brown paste
Active component	Amine salt of polyamide wax
Non-volatile	15%
Solvent	Water/ Propylene glycol- monobutyl ether
Acid value (as product)	12.5

INCORPORATION

- Make a pregel with 20 parts AQ/80 parts water and mix slowly for 20 minutes.
- Dispersing temperature is recommended between room temperature and 40°C.
- Dosage: 1.0 - 3.0 weight % as product on total formulation.
- Should be stored below 40°C.

Distributed by:

King Industries, Inc.

Science Road, Norwalk, CT 06852

Ph: 203-866-5551



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079