

*Additives for coatings and printing inks*  
**DISPARLON<sup>®</sup>**

(May 2012)

**DISPARLON<sup>®</sup> LC-955**  
(Leveling/Anti-cratering agents)

**DISPARLON LC-955** is a surface control agent based on specially prepared acrylic polymer. This product has unique properties that allow it to eliminate cratering caused by various types of dirt/stain or spray mists. They are very effective in industrial coatings where a high quality film appearance is required.

**ADVANTAGES**

- Greatly improve flow and provide excellent surface appearance.
- Eliminates cratering and film defects due to various contaminants.
- Eliminates formation of Benard-cells.
- Provides excellent re-coat property.

**APPLICATIONS**

LC-955 can be used in a wide variety of coating systems.

Application	Recommended coating type
Baking systems	Alkyd/Melamine, Acrylic/Melamine, Polyester/Melamine, Fluoropolymer/Melamine, High-solid polyester/Melamine
2-component urethane	Acrylic/Urethane, Polyester/Urethane
UV-cured systems	Urethane acrylate, Epoxy acrylate

**INCORPORATION**

Post add to finished paint is recommended.

Recommended levels : 0.5 ~ 2.0 % by weight of finished paint.

Preliminary test should be made to determine optimum level.

**TYPICAL PROPERTIES**

Appearance ..... Clear to light yellow liquid  
Non-volatile matter ..... 10 % by wt.  
Solvent ..... Solvent Naphtha / Toluene

Distributed by:  
King Industries, Inc.  
Science Road, Norwalk, CT 06852



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN  
(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

Copyright© 2009-2012 Kusumoto Chemicals, Ltd. All rights Reserved.

Ph: 203-866-5551



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

---

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See MSDS for safety handling before to use.