

*Additives for coatings and printing inks*  
**DISPARLON<sup>®</sup>**

July 2011

**DISPARLON<sup>®</sup> OX-750 HF**  
(Defoaming/Anti-popping agent)

**DISPARLON OX-750HF** is a defoaming/anti-popping agent based on specially prepared acrylic polymers, designed for baking paints such as acrylic/melamine, alkyd/melamine and acid/epoxy paint for automotive and appliance applications. Petroleum naphtha is used as the solvent in this product to comply with HAPS free regulation. This product imparts strong anti-popping properties and **OX-750HF** helps the paint make a thick film that has no surface defects.

**ADVANTAGES**

- Prevents popping in industrial coatings.
- Improves leveling.
- Silicone free. Good recoatability.

**APPLICATIONS**

**OX-750HF** is especially recommended for industrial baking paints such as acrylic/melamine, alkyd/melamine, acid/epoxy anti acid-rain paints and 2 component systems (acrylic/urethane, fluoro/urethane), giving strong anti-popping properties.

**INCORPORATION/ ADDITIVE LEVEL**

Post add and disperse homogeneously.

Additive levels ----- 0.5 ~ 1.5 % by weight of paint

**TYPICAL PROPERTIES**

Appearance .....	Colorless to light yellow liquid
Non-volatile matter .....	10 % by wt.
Specific gravity/20°C .....	0.88 g/cm <sup>3</sup>
Solvent .....	Solvent naphtha

Distributed by:  
King Industries, Inc.



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

Copyright© 2009-2011 Kusumoto Chemicals, Ltd. All rights Reserved.  
Science Road, Norwalk, CT 06852  
Ph: 203-866-5551



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

---

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See MSDS for safety handling before to use.