

Additives for coatings and printing inks
DISPARLON[®]

July 2011

DISPARLON[®] OX-883HF
(Defoaming/Anti-popping agent)

DISPARLON OX-883HF is a defoaming/anti-popping agent based on a specially prepared acrylic polymer, developed specifically for solvent based industrial heat cured top coats. Petroleum naphtha is used as the solvent in this product to comply with HAPS free regulation. **DISPARLON OX-883HF** becomes well dispersed as fine droplets in polar systems or high solids formulations. The good dispersability allows customers to use it without fear of the additive separating during circulation in coating lines and storage.

ADVANTAGES

- Long maintained defoaming/anti-popping effects on ageing
- Improves leveling and DOI
- No separation during circulation in coating line
- Good recoatability
- Silicone free. Good recoatability.

APPLICATIONS

OX-883 is recommended for industrial baking systems(alkyd/melamine, oil-free polyester/melamine, acrylic/melamine, acid/epoxy anti acid-rain paints, fluoro/melamine)and 2 component systems (acrylic/urethane, fluoro/urethane), especially for high solids industrial OEM type coating systems.

INCORPORATION

Additive level : 0.2 ~ 1.0 % by wt.
Method : Post addition on high speed dissolver is recommended.

TYPICAL PROPERTIES

Appearance Colorless to light yellow liquid
Non-volatile matter 30 % by wt.
Specific gravity/20°C 0.90 g/cm³
Solvent Solvent naphtha

Distributed by:
King Industries, Inc.



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

Copyright© 2009-2011 Kusumoto Chemicals, Ltd. All rights Reserved.
Science Road, Norwalk, CT 06852
Ph: 203-866-5551



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN

(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See MSDS for safety handling before to use.