

**NACURE<sup>®</sup> XC-269**  
Acid Catalyst



Science Road  
Norwalk, CT 06852  
United States  
+1-203-866-5551  
www.kingindustries.com

NACURE XC-269 is a specially formulated catalyst recommended for use in epoxy/phenolic based coatings.

**ADVANTAGES:** Excellent solubility  
Good package stability  
Good adhesion  
Complies with FDA 21CFR, Section 175.300 and EC Directive 2002/72/EC  
Bis Phenol A (BPA) free

<b>TYPICAL PROPERTIES:</b>	Appearance	Clear, straw liquid
	% Non-volatile	17
	Volatile	Xylene/butanol
	Weight per gallon @ 25°C (lbs)	7.6

**SOLUBILITY:** Soluble in alcohols, glycol ethers, glycols, esters and ketones. Partially soluble in aromatic solvents. Insoluble in aliphatic hydrocarbons and water.

**APPLICATIONS:** Exterior can coatings  
Interior can coatings  
Coil coatings

**TYPICAL USAGE LEVELS:** 2.0 - 5.0% as supplied on total resin solids.

**INCORPORATION:** May be added to the coating with agitation as supplied or pre-diluted with alcohol.

**SHELF LIFE:** 24 months from the date of manufacture, when stored at ambient conditions in the original container.

**HANDLING & STORAGE:** NACURE XC-269 is classified as a flammable and corrosive liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Refer to Safety Data Sheet for detailed information.

**REGULATORY:** Please refer to Section 15 of the Safety Data Sheet for information.